



Chemical Bonding Product

- Permanently Tacky
- Adhesion Promoter

Product Description

1266 Fiberglass Treatment is intended for application directly to the fiberglass in place of sanding when applying antifouling paint to the bottom of a vessel.

Product Information

Colors:	Red
Finish/Sheen:	Flat
Converter:	One Pack
Copper Content:	N/A
Volume Solids:	
Solids by Weight:	3%
Mix Ratio:	One Pack
Shipping Weight:	7 lbs.
Flash Point:	
VOC:	+500 Grams/Liter
Film Thickness:	.3-.5 mils wet
Recommended Coats:	1
Theoretical Coverage:	600 sq.ft./gal. @ recommended film thickness

Application Details

Method:	Brush, roller or spray
Induction/Sweat-in Time:	N/A
Thinner:	N/A
Cleaner:	Sea Hawk 7130
Pot Life:	N/A

Overcoating Interval

Substrate Temp.	Drying Time (Hrs)		
	Touch	Min.	Max.
73°F (23°C)	2 Hr	1 Hr	None

Consult your Sea Hawk Representative for the system best suited for surfaces to be protected.

NEW NAUTICAL COATINGS, INC.

14805 49th Street North • Clearwater, FL 33762 • 800.528.0997 • 727.523.8053 • FAX 727.523.7325

www.SeaHawkPaints.com

Limitations

Apply in good weather when air and surface temperatures are above 50°F (10°C). Surface temperature must be a least 50°F (10°C) above dew point. For optimum application properties, bring material to 70-80°F (21-27°C) temperature range prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage between 40° and 100°F (4-38°C).

Prolonged atmospheric exposure of this product may detract from performance.

Technical and application data herein is for the purpose of establishing a general guideline of the coating and proper coating application procedures. As application, environmental and design factors can vary significantly due care should be exercised in the selection, verification of performance, and use of the coating.

Surface Preparation

Paint only clean, dry surfaces. Remove all grease, oil, wax, or other foreign material using SeaHawk S-80, S-90 or detergent washing. (SSPC-SPI).

New Construction: Dependent on yard procedures, consult your Sea Hawk Representative.

Application

Apply by brush, roller or spray. Apply .5 mils wet.

EQUIPMENT

Brush: China Bristle

Roller: Solvent Resistant Roller Cover 3/8" pile smooth to medium Prewash Roller Cover to remove loose fibers prior to use.

Airless Spray: Minimum 30:1 ratio pump; 0.-011.015" orifice tip; 1/4" ID high-pressure material hose; 90 PSI line pressure; 60 mesh filter.

Thinning

N/A

Cleanup

Clean all equipment immediately after use with Sea Hawk 7130. It is a good practice to periodically flush out spray equipment during the course of the day. Frequency should depend upon amount sprayed, temperature, elapsed time including delay, etc.

Safety

Prior to use, obtain and consult the "Material Safety Data Sheet" of this product for health and safety information. Read and observe all precautionary notices on container labels.

NEW NAUTICAL COATINGS, INC.

14805 49th Street North • Clearwater, FL 33762 • 800.528.0997 • 727.523.8053 • FAX 727.523.7325

www.SeaHawkPaints.com