



ABLATIVE COPOLYMER ANTIFOULING



- Harder Ablative Formula
- Durable Finish for All Types of Vessels
- Dependable Performance

Product Description

AF-33 has been specifically formulated to be a harder ablative copolymer. The unique formulation provides a more durable multi-season antifouling for yachts, fishing vessels, tugs, barges, ferries, crab traps, and other objects that need to remain free of fouling.

Product Information

Colors:	Red, Black, others available upon request
Finish/Sheen:	Semi-Gloss
Converter:	One Pack
Copper Content:	33% (all Colors)
Volume Solids:	45.4%
Solids by Weight:	
Mix Ratio:	One Pack
Shipping Weight:	20-23 lbs./Gal.
Flash Point:	80° F
VOC:	310 Grams/Liter
Film Thickness:	5-9 mils wet equals 2.2 – 4.0 dry per coat
Recommended Coats:	2, 3 at the water line and other high wear areas
Theoretical Coverage:	328 Sq.Ft./Gal. @ 2.2 mils d.f.t.

Benefits VS. Competition

- Highest Grade of Cuprous Oxide Available (More Potent Active Ingredient)
- Harder Ablative Finish
- Better Color Consistency for Color Matching (Less Shading Issues)
- Consistent Viscosity = Better Flow and Rolling Ability in Every Gallon
- May Be Applied Over other Ablative Antifoulant Paints (See Compatibility Chart)

Application Details

Method:	Brush, roller or spray
Induction/	
Sweat-in Time:	Not Applicable
Thinner:	Sea Hawk 2033
Cleaner:	Sea Hawk 2033
Pot Life:	Not Applicable

Overcoating Interval

Substrate Temp.	Drying Time (Hrs)		
	Min.	Max.	Launch
77°F (25°C)	1 Hr	Not Critical	8 Hr

Shelf Life: 30 months when stored under cool dry conditions.

Consult your Sea Hawk Representative for the system best suited for surfaces to be protected

NEW NAUTICAL COATINGS, INC.

14805 49th Street North • Clearwater, FL 33762 • 800.528.0997 • 727.523.8053 • FAX 727.523.7325

www.SeaHawkPaints.com

Limitations

Apply in good weather when air and surface temperatures are above 50°F (10°C). Surface temperature must be a least 50°F (10°C) above dew point. For optimum application properties, bring material to 70-80°F (21-27°C) temperature range prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage between 40° and 100°F (4-38°C).

Prolonged atmospheric exposure of this product may detract from performance.

Technical and application data herein is for the purpose of establishing a general guideline of the coating and proper coating application procedures. As application, environmental and design factors can vary significantly due care should be exercised in the selection, verification of performance, and use of the coating.

Surface Preparation

Paint only clean, dry surfaces. Remove all grease, oil, wax, or other foreign material using SeaHawk S-80, S-90, or detergent washing. (SSPC-SPI).

New Construction: Dependent on yard procedures, consult your Sea Hawk Representative.

Previously Painted Surfaces: If previous coating in known and compatible (See SeaHawk Compatibility Chart) and in good condition, high pressure wash (4000PSI) with fresh water to remove all marine growth. To insure all marine growth has been removed, scuff sand with 80 grit sandpaper then remove residue prior to painting. If previous coating is in poor condition, remove antifouling by abrasive sanding, power tool cleaning, or chemical stripping with SeaHawk 1280 Marine Stripper.

Application

Apply by brush, roller or spray. Apply 5 mils wet, which will yield 2.2 mils dry per coat.

Brush: China Bristle
Roller: Solvent Resistant Roller Cover 3/8" pile smooth to medium Prewash Roller Cover to remove loose fibers prior to use.

**Airless
Spray:** Minimum 30:1 -1 GPM ratio pump; "0.015-0.026" orifice tip; 3/8" ID high-pressure material hose; 90 PSI line pressure; 60 mesh filter.

Thinning

If thinning is necessary, thin up to a maximum of 5%, with Sea Hawk 2033 only.

Cleanup

Clean all equipment immediately after use with Sea Hawk 2033. It is a good practice to periodically flush out spray equipment during the course of the day. Frequency should depend upon amount sprayed, temperature, elapsed time including delay, etc.

Safety

Prior to use, obtain and consult the "Material Safety Data Sheet" of this product for health and safety information. Read and observe all precautionary notices on container labels.

NEW NAUTICAL COATINGS, INC.

14805 49th Street North • Clearwater, FL 33762 • 800.528.0997 • 727.523.8053 • FAX 727.523.7325

www.SeaHawkPaints.com