



TBT-BASED PAINT (NON U.S.)



- Self Cleaning Copolymer Antifoulant with TBT and Copper
- The Highest Level of Protection Available Today
- Multi Season Protection for the Most Harsh Environments in the World
- No Other Comparable Paint on the Market

General Description

Islands 44 Plus was developed for the most harsh tropical environments in the world. Islands 44 Plus is a multi-seasonal self-polishing paint. It has a high load of copper and tin that will ensure maximum protection against marine growth. Islands 44 Plus is also available in a hard formulation. It has the same properties, just a little harder, for our "Mega" yacht customers.

Product Information

Colors:	Red, Black, Blue, Green, Teal, Plum, Maroon
Finish/Sheen:	Gloss
Converter:	One Pack
Copper Content:	47%
Tributyltin Methacrylate:	10.48%
Tributyltin Oxide:	.60%
Volume Solids:	69% ± 2%
Solids by Weight:	
Mix Ratio:	One Pack
Shipping Weight:	14.5 lbs./gal.
Flash Point:	100° F
VOC:	400 Grams/Liter
Film Thickness:	5 mils wet equals 3.45 dry per coat
Recommended Coats:	2 heavy coats on entire hull and 3 at waterline and other high wear areas
Theoretical Coverage:	400 sq.ft./gal. @ recommended film thickness

Benefits VS. Competition

- The Only Tin Paint Available on the Market
- (No Other Comparable Product)
- Highest Level of Antifoulant Protection
- Highest Quality Grade of Cuprous Oxide Available (More Potent Active Ingredient)
- Better Color Consistency for Color Matching (Less Shading Issues)
- Consistent Viscosity = Better Flow and Rolling Ability in Every Gallon

Application Details

Method:	Brush, roller or spray
Induction/	
Sweat-in Time:	Not Applicable
Thinner:	Sea Hawk 2031
Cleaner:	Sea Hawk 2031
Pot Life:	Not Applicable

Overcoating Interval

Substrate Temp.	Drying Time (Hrs)			
	Touch	Min.	Max.	Launch
73°F (23°C)	3 Hr	1 Hr	N/A	12 Hr
95°F (35°C)	1 Hr	1 Hr	N/A	12 Hr

Consult your Sea Hawk Representative for the system best suited for surfaces to be protected.

NEW NAUTICAL COATINGS, INC.

14805 49th Street North • Clearwater, FL 33762 • 727.523.8053 • 800.528.0997 • FAX 727.523.7325

www.SeaHawkPaints.com

Limitations

Apply in good weather when air and surface temperatures are above 50°F (10°C). Surface temperature must be a least 50°F (10°C) above dew point. For optimum application properties, bring material to 70-80°F (21-27°C) temperature range prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage between 40° and 100°F (4-38°C).

Prolonged atmospheric exposure of this product may detract from performance.

Technical and application data herein is for the purpose of establishing a general guideline of the coating and proper coating application procedures. As application, environmental and design factors can vary significantly due care should be exercised in the selection, verification of performance, and use of the coating.

Surface Preparation

Paint only clean, dry surfaces. Remove all grease, oil, wax, or other foreign material using SeaHawk S-80, S-90, or detergent washing. (SSPC-SPI).

New Construction: Dependent on yard procedures, consult your Sea Hawk Representative.

Previously Painted Surfaces: If previous coating in know compatible (See SeaHawk Compatibility Chart) and in good condition, scuff sand with 80 grit sandpaper then solvent clean with SeaHawk S-80 Wax "N" Greaser to remove residue. In poor condition remove antifouling with SeaHawk 1280 Marine Stripper.

* Islands 44 Plus can be applied over any other bottom paint except soft ablatives. Previous soft ablatives must be removed or 2 coats of SeaHawk Island Prime 1283 Barrier Sealer applied before application.

Application

Apply by brush, roller or spray. Apply 5 mils wet, which will yield 3.45 mils dry per coat.

Brush: China Bristle
Roller: Solvent Resistant Roller Cover 3/8" pile smooth to medium Prewash Roller Cover to remove loose fibers prior to use.

Airless Spray: Minimum 33:1 -2 GPM ratio pump; "0.017-0.026" orifice tip; 3/8" ID high-pressure material hose; 90 PSI line pressure; 60 mesh filter.

Thinning

If thinning is necessary, thin up to a maximum of 10%, with Sea Hawk 2031 only.

Cleanup

Clean all equipment immediately after use with Sea Hawk 2031. It is a good practice to periodically flush out spray equipment during the course of the day. Frequency should depend upon amount sprayed, temperature, elapsed time including delay, etc.

Safety

Prior to use, obtain and consult the "Material Safety Data Sheet" of this product for health and safety information. Read and observe all precautionary notices on container labels.

NEW NAUTICAL COATINGS, INC.

14805 49th Street North • Clearwater, FL 33762 • 727.523.8053 • 800.528.0997 • FAX 727.523.7325

www.SeaHawkPaints.com