

## **Premium Marine Grade Gel Coat**

- Chemical Resistant
- Patch Existing Gelcoat, New Construction
- Fiberglass Repair









### **Product Description**

Sea Hawk Gelcoat is a premium quality isophthalic NPG gelcoat formulated to meet rigid requirements in the boating, transportation, and sanitary applications. Meets American National Standard for plastic bath tubs, show receptors, and shower stalls. (ANSI Z124.1, .2005, Sec. 6.1). May be used to patch, re-gelcoat, or new application. Common uses include boats, RV's, showers, tubs, pools, and more.

#### **Product Information**

**Colors:** White-8115, Black-2017, Jade Mist Green-4089 Sea Foam-4256, Flag Blue,-5002, Ice Blue-5004, Marlin Blue-5011, Teal-5328, Clear-6000, Orange Tooling-7000, Toreador Red-7161, Vivid Red-7367, Matterhorn White-8003, Whisper Gray-8035, Fighting Lady Yellow-9093, Federal Yellow-9298,

Sizes: Quart, Gallon, 5 Gallon Pail

Finish/Sheen: Gloss

**Shipping Weight:** 9-11 Lbs./Gal. (Depending on Color)

Flash Point: 82-88° F

**VOC:** 35-42%

Typical Film Thickness: 18 ±2 mils.

Catalyst Level (MEKP): 1.2% Minimum - 3.0% Maximum

Gel Time at 1.8% MEKP Catalyst @ 77°F: 10-17 minutes

Theoretical Coverage: Approx. 48-52 Sq.Ft./Gal. @ typical

film thickness

**Storage:** Avoid prolonged exposure at temperatures above 85°F and to direct sunlight. Increased storage temperatures will negatively effect shelf life. Store in a cool place.

**Shelf Life:** 270 Days when stored under cool, dry conditions.

#### **Features and Benefits**

- Premium Marine Grade Gelcoat
- Ready to Use, Easy to Spray, Sag Resistant
- High Gloss Retention
- Excellent Weatherability and Chemical Resistance
- Resistance to water blistering

## **Application Controls**

**Method:** This product may be applied by airless and conventional spray, solvent resistant rollers and brushes for small areas only.

#### **Dry Times and Overcoating Intervals In Hours:**

Substrate Temp.	Overcoat- ing	Sand/ Compound	Max
73°F (23°C)	2 hr	12 hr	Not Critical
95°F (35°C)	1 hr	6 hr	Not Critical

Do not apply directly over painted surface.

#### Catalyzing with MEKP:

	MEKp (Catalyst) Warmer ← Temperature Conditions ← Cooler								
	1.2% Minimum		1.8% 77F (Ideal)		3% (Maximum)				
Size	сс	οz	сс	oz	сс	oz			
1 pint	5	0.19	8	0.25	14	0.50			
1 quart	9	0.33	16	0.50	28	1			
1 gallon	37	1.25	65	2.13	112	4			



## **Gel Coat Preparation**

Stir container thoroughly before using. Add any additives such as Sea Hawk 7125 MEK Gelcoat Thinner, Sea Hawk Patch Aid 8185, or colorants (tints) prior to catalyzing with MEKP Catalyzer.

# **Surface Preparation**

Gelcoat over clean, dry surfaces. Remove all grease, oil, wax, or other foreign material by using Sea Hawk S-80 Wax N Grease Killer. All surfaces must be sanded. Do not apply directly over paint.

#### **Additives**

**Patch Aid 8185:** Add 25-33% Sea Hawk Patch Aid 8185 when applying gelcoat for small repairs, to improve the working properties of traditional gelcoat spray patches.

**Wax Additive:** Do not add wax additive if using Patch Aid. Path Aid already contains a wax additive. If not using Sea Hawk 8185 Patch Aid, then you may add up to 4oz of Sea Hawk 8140 Wax Additive per gallon for tack free surface on final coat.

**Tinting:** Sea Hawk Gelcoat may be tinted using Sea Hawk colorants designed for use in Sea Hawk resins and gel coats. Do not use more than 1 oz tint per quart.

**Catalyzing Gelcoat with MEKP:** The catalyst level (MEKP) should not exceed 3.0% or fall below 1.2 for proper cure. Ideal range is 1.8% @ 77°F. Gel time at 1.8% MEKP is 10-17 minutes. This time element is dependent on material temperature, room temperature, humidity, air movement, and catalyst concentration. Gelcoat should not be used when temperature conditions are below 60°F, as curing may be adversely affected. See Catalyst mixing ratios on page 1.

### **Application**

Best when applied by spray. Gelcoat delivery rate of no more than 2.5 pounds per minute with conventional air atomized spray, and no more than 4 pounds per minute with airless equipment. For more detailed gelcoat application please go to www.seahawkpaints.com/gelcoat

**Storage:** Avoid prolonged exposure at temperatures above 85°F and to direct sunlight. Store in a cool, dry place. This material will remain stable for three months when stored at 73°F or below. Warmer temperatures will reduce the usage life of this product. Keep away from heat, sparks, and flame. Keep container tightly closed. Prevent contamination with foreign material. Store below 100°F, out of sunlight. Avoid contact and wear protective clothing including goggles and gloves. Use with adequate ventilation.

#### **Limitations:**

Apply in good weather when air and surface temperatures are above  $60^{\circ}F$  ( $16^{\circ}C$ ). Surface temperature must be a least  $60^{\circ}F$  ( $16^{\circ}C$ ) above dew point. For optimum application properties, bring material to  $70\text{-}80^{\circ}F$  ( $21\text{-}27^{\circ}C$ ) temperature range prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage between  $40^{\circ}$  and  $74^{\circ}F$  ( $4\text{-}23^{\circ}C$ ). Prolonged atmospheric exposure of this product may detract from performance and reduce shelf life. Technical and application data herein is for the purpose of establishing a general guideline of the coating and proper coating application procedures. As application, environmental and design factors can vary significantly due care should be exercised in the selection, verification of performance, and use of the coating.

# **Gel Coat** *ISO/NPG Series*





# **Application Data**

**Mixing:** Stir container thoroughly before use. Do not over mix.

**Thinning:** If necessary, maximum 10% Sea Hawk 7125 MEK Gelcoat Thinner. Do not thin when using Patch Aid 8185.

**Clean Up:** Acetone or MEK

**Pot Life:** 10-17 Minutes depending on atmospheric conditions and MEKP Catalyst Ratio.

**Brush/Rolling:** (For smaller repairs / applications only) Solvent Resistant Roller Cover 3/16" pile (nap), or Natural bristle brush. **Spraying recommended.** 

**Spray: Airless or Conventional:** 2.0-2.5 orifice tip. Use ES Manufacturing Gelcoat Spray Gun G830, ES-G100, or equivalent.

**Safety:** Prior to use, obtain and consult the "Material Safety Data Sheet" of this product for health and safety information. Read and observe all precautionary notices on container labels.

Revision Date 2/2012