

### Chemical Bonding Product

- Permanently Tacky
- Adhesion Promoter



### Fiberglass Treatment

Use when sanding  
is not an option



OVER  
35  
YEARS

### PRODUCT DESCRIPTION

1266 Fiberglass Treatment is intended for application directly to the fiberglass in place of sanding when applying antifouling paint to the bottom of a vessel.



### PRODUCT INFORMATION

- Colors:** Red
- Finish/Sheen:** Flat
- Converter:** One Pack
- Copper Content:** N/A
- Solids by Volume:** 3%
- Solids by Weight:** 4%
- Mix Ratio:** One Pack
- Shipping Weight:** 7 Lbs.
- Flash Point:**
- VOC:** +500 Grams/Liter
- Film Thickness:** .3-.5 mils wet (7.6-12.7 microns)  
0.01-0.02 mils dry (0.25-0.51 micron)
- Recommended Coats:** 1
- Theoretical Coverage:** 2,406 sq. ft./gallon at 0.02 mil dry  
(58.8 sq. m/liter at 0.51 micron dry)

### APPLICATION DETAILS

- Method:** Brush, Roller or Spray. Apply .5 mils wet (12.7 microns)
- Induction Time:** Not Applicable
- Thinner:** Sea Hawk 2033
- Cleaner:** Sea Hawk 2033
- Pot Life:** Not Applicable

### OVERCOATING INTERVAL

Drying Time (Hrs)

Substrate Temp.	Overcoating Time		Launch
	Min	Max	Min
73°F (23°C)	1 hrs	N/A	12 hrs



# 1266 Non-Sanding Primer

## Technical Data Sheet

### EQUIPMENT

**Brush:** China Bristle

**Roller:** Solvent Resistant Roller Cover 3/8" pile smooth to medium Prewash Roller Cover to remove loose fibers prior to use.

### AIRLESS

**Spray:** Minimum 28:1 ratio pump; 0.021"-0.026" (533-660 microns) orifice tip; 3/8" ID high-pressure material hose; 90 PSI line pressure; 60 mesh filter.

### THINNING

N/A

### CLEANUP

Clean all equipment immediately after use with Sea Hawk 7130. It is a good practice to periodically flush out spray equipment during the course of the day. Frequency should depend upon amount sprayed, temperature, elapsed time including delay, etc.

### Safety

Prior to use, obtain and consult the "Safety Data Sheet" of this product for health and safety information. Read and observe all precautionary notices on container labels

### Surface Preparation

Paint only clean, dry surfaces. Remove all grease, oil, wax, or other foreign material using SeaHawk S-80, S-90, or detergent washing. (SSPC-SPI).

**New Construction:** Dependent on yard procedures, consult your Sea Hawk Representative.

### Limitations

Apply in good weather when air and surface temperatures are above 50°F (10°C). Surface temperature must be a least 50°F (10°C) above dew point. For optimum application properties, bring material to 70-80°F (21-27°C) temperature range prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage between 40° and 100°F (4-38°C).

Prolonged atmospheric exposure of this product may detract from performance.

Technical and application data herein is for the purpose of establishing a general guideline of the coating and proper coating application procedures. As application, environmental and design factors can vary significantly due care should be exercised in the selection, verification of performance, and use of the coating.